Shanghai Leadgo-Tech Co.,Ltd.

地址: 上海浦东康桥东路1365弄18号 POST: 201319 ADD: 18#, NO.1365,East Kangqiao Road.Pudong Area.Shanghai 201319 China TEL:0086(0)21 68183116 68183117 68183118 Fax:0086(0)21 68183100



R60

Document NO. LG-YF-PP-45 Edition A/O

DESCRIPTION

R60 is an excellent porous Nylon66 peel ply or release fabric, is our tightest weave nylon peel ply that produces a "fine" texture. It has been heat scoured and stabilized at high temperature.

R60 is free of any release agent or pollution and can be used directly on the surface of the part.

R60 and generally a Nylon peel ply should not be used on phenolic resin. Make a trial or call our technical team for further advice.

◆ CHARACTERISTIC

- · Smooth surface without any impurities
- · Non-coated nylon peel ply with tight weave

◆ PROPERTIES

Specifications		
Material	PA66	
Colour	White	
Thickness/in	0.004 (106um)	
Width/in	60 (1520mm)	
Weight[g/m²]	62	
Maximum Use Temperature/°F	390 (200℃)	
Release agent	No	

Physical Properties		
Tensile Strength (MD) [N/2.0in]	GB/T 3923.1	≥650
Tensile Strength (TD) [N/2.0in]	GD/1 3923.1	≥550

♦ NOTES

Maximum use temperature is dependant upon the duration at maximum temperature and is process specific.

◆ STORAGE

◆ R60 is packed in roll. Recommend being packed in polyethylene bag and wrapped in clean cardboard sleeve or any other materials which have the same function, stored in a clean and relative humidity environment about 30%-70%RH and 40 -80°F (5-25°C).

Characteristics given in this TDS are for information only and help to make a choice. End users should validate the use of products according their own tests and findings. In any case these values or information shall be taken to engage responsibility of LEADGO companies. Model specifications, product information is subject to change without any further notice.